




Alloy		OBSERVATION	RESULT
AMS 4911 Blank Control	# 1	No evidence of cracking.	AMS 4911 Titanium sheet meets acceptability and sensitivity criteria
	# 2	No evidence of cracking.	
	# 3	No evidence of cracking.	
AMS 4911 3% Salt Control	# 1	Cracking evident.	
	# 2	Cracking evident.	
	# 3	Cracking evident.	
AMS 4911 Candidate Solution	# 1	No evidence of cracking.	Conforms
	# 2	No evidence of cracking.	Conforms
	# 3	No evidence of cracking.	Conforms
AMS 4916 Blank Control	# 1	No evidence of cracking.	AMS 4916 Titanium sheet meets acceptability and sensitivity criteria
	# 2	No evidence of cracking.	
	# 3	No evidence of cracking.	
AMS 4916 100 ppm Salt Control	# 1	Cracking evident.	
	# 2	Cracking evident.	
	# 3	Cracking evident.	
AMS 4916 Candidate Solution	# 1	No evidence of cracking.	Conforms
	# 2	No evidence of cracking.	Conforms
	# 3	No evidence of cracking.	Conforms

Respectfully submitted,



Patricia D. Viani, SMI Inc.